

1422A TYVEK® CONTINUOUS FORM TUBING

Typical Application & Characteristics

- Recommended for Steam Sterilization of Pharmaceutical Production Equipment
- Cost Effective
- Tyvek® on Both Sides for Maximum Penetration During Sterilization
- Minimizes the Use of Autoclave Tape
- Fast and Consistent for Equipment Preparation Area
- Creates Strong Seals When Heat Sealed
- Hydrophobic
- Resists Tearing and Punctures
- Superior Microbial Barrier
- Lint-Free – Category 1 (Helmke Drum)
- Manufactured and Packaged in a Controlled Cleanroom Environment
- Certificates of Conformance Sent with Shipments

PROPERTY	UNITS	TEST METHOD	Typical Values 1422A Tyvek®
Seal Strength	N/mm	F-88	>.78
Basis Weight	g/m ²	EN ISO 536	41
Total Thickness	μ	EN 20534	130
Air Permeability	s	ISO 5636-5	20
Water Vapor Permeability	G/M2/24 HR	ASTM 398	1700
Hydrostatic Head	cm H ₂ O	ISO 811	120
Trapezoidal Tear MD/CD	N	ISO 9073-4	26.1/30.6
Linting Propensity	Rating	BS 6909 (Shirley Method 21)	Pass Rating: Excellent
Burst Resistance	kPa	ISO 2960 (50 cm ²)	108
Puncture Resistance	N	EN 863	10.8
Melting Point	C °		135

Item Code	Dimensions
TUBT2A02	2"
TUBT2A03	3"
TUBT2A04	4"
TUBT2A05	5"
TUBT2A06	6"
TUBT2A08	8"
TUBT2A10	10"
TUBT2A12	12"
TUBT2A15	15"
TUBT2A16	16"
TUBT2A24	24"
TUBT2A28	28"
TUBT2A30	30"
TUBT2A40	40"

KEYSTONE

CLEANROOM PRODUCTS

1591 Hylton Road
Pennsauken, NJ 08110
(800) 663-5439
www.KeystoneCRP.com